

2020 NITRILE

POWDER FREE NITRILE MEDICAL EXAMINATION GLOVES

Standards Met:

ASTM D6319[†]
 ASTM D6978-05^{††}

Attributes:

- Not made with natural rubber latex
- Powder Free Blue Nitrile
- Ambidextrous
- Textured fingertip
- Non-sterile
- Single use only

Dimensions:


Box dimensions: 23 cm x 12.5 cm x 8.0 cm
 Box count: 200 gloves per box (by weight)
 Case pack: 10 boxes per case



PROTECTION
against
FENTANYL^{†††}



SPECIFICATIONS		SMALL	MEDIUM	LARGE	X-LARGE
Item Number		#51301	#51302	#51303	#51304
Width of Palm (mm)		85 ± 5	95 ± 5	105 ± 5	115 ± 5
Total Length (mm)		230 min.	230 min.	230 min.	230 min.
Thickness: Palm (mm)		0.07 ± 0.03	0.07 ± 0.03	0.07 ± 0.03	0.07 ± 0.03
Thickness: Finger (mm)		0.08 ± 0.03	0.08 ± 0.03	0.08 ± 0.03	0.08 ± 0.03
Thickness: Cuff (mm)		0.07 ± 0.03	0.07 ± 0.03	0.07 ± 0.03	0.07 ± 0.03
Tensile Strength (MPa)	Before Aging	17 min.	17 min.	17 min.	17 min.
Tensile Strength (MPa)	After Aging	14 min.	14 min.	14 min.	14 min.
Elongation (%)	Before Aging	550 min.	550 min.	550 min.	550 min.
Elongation (%)	After Aging	500 min.	500 min.	500 min.	500 min.



Made in China

The information provided is given in good faith and believed to be accurate, but no warranty or guarantee is given or implied. Conditions of use under which the product is being applied will vary from the conditions of laboratory testing. [†]Standard Specification for Nitrile Examination Gloves ^{††}Standard Practice for assessment of Resistance of Medical Gloves to Permeation by Chemotherapy Drugs ^{†††}Permeation Testing (ASTM D6978-05) for **Fentanyl Citrate Injection**, demonstrates no breakthrough for up to 240 minutes.

MP-REF-51300B
 Rev.1: 2021-02-05