maxill Gloves

maxill inc., St. Thomas, Ontario N5R 6C8
www.maxill.com 1-800-268-8633

maxill Nitrile

POWDER FREE NITRILE MEDICAL EXAMINATION GLOVES

Standards Met:

ASTM D6319†
ASTM D6978-05††
ISO 16604:2004†††

PROTECTION *against* FENTANYL††††




Attributes:

- Not made with natural rubber latex, BBP, BPA or DPB
- Powder Free Nitrile
- Ambidextrous
- Short beaded cuff
- Textured fingertip
- Non-sterile
- Single use only

Dimensions:

Box dimensions: 24.0 cm x 12.5 cm x 7.0 cm
Box count: 100 gloves per box
Case pack: 10 boxes per case

SPECIFICATIONS		SMALL	MEDIUM	LARGE	X-LARGE
Item Number		#51141	#51142	#51143	#51144
Width of Palm (mm)		80 - 90	90 - 100	100 - 110	110 - 120
Total Length (mm)		240 min.	240 min.	240 min.	240 min.
Thickness: Cuff (mm)		0.06 min.	0.06 min.	0.06 min.	0.06 min.
Thickness: Palm (mm)		0.08 min.	0.08 min.	0.08 min.	0.08 min.
Thickness: Finger (mm)		0.10 min.	0.10 min.	0.10 min.	0.10 min.
Tensile Strength (MPa)		14 min.	14 min.	14 min.	14 min.
Force at Break (N)		6 min.	6 min.	6 min.	6 min.
Elongation (%)	Before Aging	500 min.	500 min.	500 min.	500 min.
Elongation (%)	After Aging	400 min.	400 min.	400 min.	400 min.



Made in Malaysia

The information provided is given in good faith and believed to be accurate, but no warranty or guarantee is given or implied. Conditions of use under which the product is being applied will vary from the conditions of laboratory testing. †Standard Specification for Nitrile Examination Gloves ††Standard Practice for assessment of Resistance of Medical Gloves to Permeation by Chemotherapy Drugs †††Clothing for protection against contact with blood and body fluids – Determination of resistance of protective clothing materials to penetration by blood-borne pathogens – Test method using Phi-X 174 bacteriophage. ††††Permeation Testing (ASTM D6978-05) for **Fentanyl Citrate Injection**, demonstrates no breakthrough for up to 240 minutes.

MP-REF-51140B
Rev.2: 2019-05-07